

[54] NON-ANTIGENIC COLLAGEN AND ARTICLES OF MANUFACTURE

[76] Inventors: Edward E. Luck, 216 Robin Way, Menlo Park, Calif. 94025; John R. Daniels, 842 Las Casas, Pacific Palisades, Calif. 90272

[21] Appl. No.: 532,572

[22] Filed: Sep. 15, 1983

Related U.S. Application Data

[60] Continuation-in-part of Ser. No. 144,705, Apr. 28, 1980, now Defensive Publication No.

[51] Int. Cl.³ C08L 89/06; C07G 7/00

[52] U.S. Cl. 106/161; 204/158; 210/637; 210/644; 210/645; 260/123.7; 264/202

[58] Field of Search 260/118, 123.7; 106/161, 155; 210/637, 644, 645; 204/158; 264/202

[56] References Cited

U.S. PATENT DOCUMENTS

2,919,999	1/1960	Reissman et al.	106/161
2,920,000	1/1960	Hochstadt et al.	106/161
3,131,130	4/1964	Oneson et al.	106/161
3,303,038	2/1967	Klevens	106/155
3,314,861	4/1967	Fujii	260/117
3,503,877	3/1970	Berry	210/644
3,949,073	4/1976	Daniels et al.	424/177
4,089,333	5/1978	Utsuo et al.	128/156
4,140,537	2/1979	Luck et al.	106/161
4,233,360	11/1980	Luck et al.	106/155

FOREIGN PATENT DOCUMENTS

903975 4/1960 United Kingdom .

Primary Examiner—Theodore Morris

[57] ABSTRACT

Collagen, available from domestic animals, is freed of noncollagen proteins, glycosaminoglycans and lipids by enzymatic treatment with a proteolytic enzyme to yield a product which is soluble in dilute acidic aqueous solutions (collagen in solution—CIS). The naturally occurring collagen is modified by removal of certain terminal peptide chains, which are described as telopeptides. The modified collagen, so derived, is described as atelopeptide collagen. Native collagen is immunogenic, while atelopeptide collagen is nonimmunogenic or possessed of a negligibly low level of immunogenicity.

The collagen in solution is then treated according to a specific regimen under conditions whereby the collagen slowly separates from solution while exposed to mild shear forces. This procedure results in the formation of a fibrous precipitate composed of regularly ordered fibers of collagen possessed of a rope-like structure. These resulting aggregates are referred to as native fibrous micropolymers (NFM). Once the regimen or procedure is completed, and the fiber mass has been formed, the fibrous micropolymers may be freed of salt, taken up in a different solution or modified. For example, cross-links may then be introduced to stabilize the fibers. The products find wide use as packing, membranes, fibers, bags, supports, integuments, and are especially suitable for biologic implantation or application.

14 Claims, No Drawings